



Anchor-Weld N150 (Red or Clear)

Spray Grade High Heat Resistant Contact Adhesive

DESCRIPTION

Anchor-Weld N150 Contact Adhesive is a solvent based (flammable), high solids, high heat resistant spray grade adhesive, specifically formulated to stay in solution in hot and cold conditions.

Anchor-Weld N150 Contact Adhesive exceeds the Australian Standard 2131-1978 heat resistance test, making it an ideal adhesive for use in heat prone areas. It is used for bonding decorative plastic laminates, aluminum, mild steel, wood, wood veneer, particleboard, plywood, gypsum wallboard, linoleum, galvanized steel, paper honey-comb, rigid polyurethane foam and other similar materials in the manufacture of counter tops, table tops, desk tops, vanities, furniture, sandwich panels, doors, cabinets, partitions, wall panels and other laminated products. Not recommended for bonding polystyrene foam, materials to copper or for exterior use.

SURFACE PREPARATION

Surfaces must be clean, dry and free from oil, dust and other foreign materials. Wipe metal with *Anchor-Weld 900 Cleaner/Thinner* before applying adhesive as mill process oil is often found on metal. Mould release powders are often found on rubber and plastic castings.

APPLICATION

Anchor-Weld N150 Contact Adhesive is perfect for use with Mid West, Evans and other postforming equipment. It can also be applied using standard spray equipment such as 200 litre pumps, 20 litre pressure pots and one litre suction cup guns. Apply adhesive to approximately 80% of the surface area to be bonded with an additional build up of adhesive toward edges. Spray adhesive to both surfaces. Allow adhesive to become touch dry. This will take approximately 10-15 minutes depending on atmospheric conditions and can be tested by placing the knuckles into the adhesive which should feel tacky but not transfer to the knuckles. Two or more coats may be required on porous surfaces. Surfaces should be joined within 45 minutes after application. If the surfaces are not joined within this time, they can be reactivated by applying another coat of adhesive. A minimum of 276KPa (40psi) bond pressure is recommended for best results. Pressure should be applied by using a pinch roller or *Roberts Hand Roller 10-955*, working from the centre toward edges to remove all air bubbles.

CLEAN UP

To clean up equipment and adhesive spills use *Anchor-Weld 900 Cleaner/Thinner*. *Anchor-Weld 900* is **not** recommended for removing adhesive from vinyl or lacquered surfaces.

Thinning is not recommended.

TYPICAL PROPERTIES

Appearance:	Red or Clear
Base:	Neoprene rubber
Solids:	Approximately 18%
Viscosity :	Thin syrup
Shelf Life:	Approximately 1 year in sealed container at 20°C
Flash Point:	Less than 0°C
Dry Time/ Tack Up:	Approximately 10-15 minutes at 20°C
Open Time:	Approximately 45 minutes
Coverage:	Approximately 6m ² per litre
Available in	200L and 20L
Heat Resistance -	exceeds 195°C

NOTE

The two most common causes of bond failure are:

1. Insufficient adhesive
2. Insufficient pressure

SAFETY INSTRUCTIONS

Product is flammable.

Storage - Store inside where possible out of direct sunlight. Storage areas to be well ventilated and kept at a maximum of 20°C. Refer to local council and government regulations.

IN USE:

Respiratory Protection - Not required if ventilation is adequate, otherwise use a half face vapour filter.

Ventilation - General dilute ventilation of sufficient volume and pattern to keep vapour concentration below 300p.p.m.

Protective Gloves - Solvent resistant

Eye Protection - Safety glass with side shield.

Disclaimer: Information given on this data sheet, is to the best available knowledge of the manufacturer, true and correct. However owing to the diverse nature of applications, conditions, and materials used, no guarantee either expressed or implied, can be given.

Enquiries should be directed to RLA Polymers Pty Ltd.
