



## RL2109 Carboxylated Styrene Butadiene Copolymer Latex

### APPLICATION

Application to textiles such as woven carpets and needle punch fabrics where a medium to firm handle is required.

### SPECIFICATIONS

#### Total solids content

RLA Test Method QC 204 51.0% ± 1.0%

#### Viscosity

RLA Test Method QC 205 Brookfield RVT  
Spindle 1  
Speed 10  
140 ± 40 cps

#### pH

RLA Test Method QC 207 7.0 ± 8.0

### STORAGE & HANDLING

Material should remain usable for 12 weeks from delivery date providing material is stored in accordance with listed instructions. (Refer to Material Safety Data Sheet).

### HEALTH & SAFETY

Refer to Material Safety Data Sheet.

Issued: May 2007

The application, use and processing of our products is the responsibility of the user. Any technical or other advice, information or data provided by us, whether verbally, in writing or by way of trials or tests, is given without guarantee or warranty. Refer to Material Safety Data Sheets for information on Storage & Handling, Health and Safety, and Transport.

### RLA POLYMERS PTY LTD

ACN 004 709 915

215 Colchester Road, Kilsyth, Victoria 3137 Australia  
P.O. Box 147, Kilsyth, Victoria 3137 Australia  
Telephone: (03) 9728 1644 • Facsimile: (03) 9728 6009  
E-mail: info@rlapolymers.com.au

 A British Vita Group Company



67 Dalgety Drive (P.O. Box 97-575)  
Manukau City, Auckland, New Zealand  
Telephone: (9) 268 0301  
Facsimile: (9) 268 0305

RLA 044B